

IN THE CLAIMS:

Please cancel claims 14 through 40.

1. (PREVIOUSLY PRESENTED) A polymer composition:
a first component being an adipic polyester;
a second component being a natural polymer; and
a third component being a thermoplastic polyester, wherein the first component,
second component and third component are combined to form the polymer composition.
2. (PREVIOUSLY PRESENTED) A polymer composition as set forth in claim
1 wherein the natural polymer is starch.
3. (PREVIOUSLY PRESENTED) A polymer composition as set forth in claim
2 wherein the starch is granular.
4. (PREVIOUSLY PRESENTED) A polymer composition as set forth in claim
1 wherein the hydroxy-functional polymer is a poly(hydroxy ester ether)(PHEE).
5. (PREVIOUSLY PRESENTED) A polymer composition as set forth in claim
1 wherein the thermoplastic polyester is one from a group comprising poly(lactic acid), cellulose
acetate, polycaprolactone, polyhydroxy(butyrate-co-valerate)(PHBV), poly(butylene succinate
adipate), poly(butylene succinate), aliphatic-aromatic copolymer, and poly(ethylene
terphthalate)(PET).

6. (PREVIOUSLY PRESENTED) A polymer composition as set forth in claim 1 wherein the second component is present in an amount up to about 74 wt.%.

7. (PREVIOUSLY PRESENTED) A polymer composition as set forth in claim 1 wherein the first component is present in an amount up to about 40 wt.%.

8. (PREVIOUSLY PRESENTED) A polymer composition as set forth in claim 1 wherein the third component is present in an amount up to about 80 wt.%.

9. (PREVIOUSLY PRESENTED) A polymer composition as set forth in claim 1 including a fourth component from a group comprising an external lubricant, nucleating agent and plasticizer.

10. (PREVIOUSLY PRESENTED) A polymer composition as set forth in claim 1 wherein the natural polymer has a moisture content of less than about 15 wt.%.

11. (PREVIOUSLY PRESENTED) A polymer composition as set forth in claim 1 wherein the polymer composition is biodegradable.

12. (PREVIOUSLY PRESENTED) A polymer composition as set forth in claim 1 wherein the polymer composition is processed into an article that keeps its shape at temperatures of up to and more than about 100°C.

13. (PREVIOUSLY PRESENTED) A polymer composition as set forth in claim 1 wherein the polymer composition is annealed to increase high temperature stability.

14. (CANCELED)

15. (CANCELED)

16. (CANCELED)

17. (CANCELED)

18. (CANCELED)

19. (CANCELED)

20. (CANCELED)

21. (CANCELED)

22. (CANCELED)

23. (CANCELED)

24. (CANCELED)

25. (CANCELED)

26. (CANCELED)

27. (CANCELED)

28. (CANCELED)

29. (CANCELED)

30. (CANCELED)

31. (CANCELED)

32. (CANCELED)

33. (CANCELED)

34. (CANCELED)

35. (CANCELED)

36. (CANCELED)

37. (CANCELED)

38. (CANCELED)

39. (CANCELED)

40. (CANCELED)

41. (ORIGINAL) A polymer composition:

a first component being a hydroxy-functional polymer;

a second component being a natural polymer; and

a third component being a thermoplastic polyester, wherein the first component, second component and third component are combined to form the polymer composition and wherein the hydroxy-functional polymer is a poly(hydroxy ester ether)(PHEE) in an amount of about 1 wt.%.